

<b>Plum Creek AB Marine Grade Plywood</b>	
<b>SPECS</b>	<ul style="list-style-type: none"> <li>• Slow growth inland Douglas Fir and Western Larch yield fine-grained, smooth faces</li> <li>• All Group 1, Struc 1 Species</li> </ul>
<b>FACES</b>	<ul style="list-style-type: none"> <li>• "A" grade faces shall be limited to a total of nine repairs in a 4' x 8' panel.</li> </ul>
<b>BACKS, CENTERS &amp; CORES</b>	<ul style="list-style-type: none"> <li>• All backs, centers and inner plies shall be "B" grade or better and shall be full length and full width.</li> <li>• Neither edge of a panel shall have any cross band gap or edge splits in excess of 1/8" wide or 4 in number. No inner ply laps are allowed.</li> </ul>
<b>CONSTRUCTION &amp; THICKNESS</b>	<p><b>Thickness Ply count</b></p> <p>1/4"     3 Ply</p> <p>3/8"     4 Ply</p> <p>1/2"     5 Ply</p> <p>5/8"     7 Ply</p> <p>3/4"     7 Ply</p> <ul style="list-style-type: none"> <li>• Panel thickness to 1 1/2"</li> <li>• Solid long length to 102"</li> <li>• Scarfed lengths to 16'</li> <li>• Full thick</li> <li>• Tongue and groove available on 5/8" - 1 1/8"</li> </ul>